

MATERIAL SELECTION GUIDE FOR SELECTIVE LASER SINTERING - SLS

	DuraForm TPU	DuraForm Flex	DuraForm EX / DuraForm ProX EX BLK	DuraForm PA / DuraForm ProX PA	DuraForm GF / DuraForm ProX GF	DuraForm HST / DuraForm ProX HST	CastForm PS	DuraForm FR1200 / DuraForm ProX® FR1200	DuraForm ProX® AF+
Base Material	Thermoplastic Polyurethane	Thermoplastic Elastomer	Nylon/PA11	Nylon/PA12	Nylon/PA12	Nylon/PA12	Polystyrene	Nylon/PA12	Nylon/PA12
Stiff / rigid					•••	••••			•••
Non-rigid / durable-tough			••••	•••				•••	
Elastomeric / rubber-like	••••	••••							
High-temperature resistance					• • •	•••			•••
High elongation	••••	••••	•••	• • •					
High-impact strength			••••	•••		• • •			• • •
Accuracy	•••	•••	• • •	••••	•••	•••	••••	•••	•••
Surface finish	• • •	• • •	•••	••••	• • •	• • •	•••	•••	•••
Color	White	White	Black or White	White	Pale grey	Pale grey	White	White	Metallic grey

RECOMMENDED APPLICATIONS											
Production parts	•••	•••	••••	••••	••••	••••		••••	••••		
Snap fits / living hinges			••••	•••							
Automotive design			•••	••••	•••	•••			••••		
Aerospace parts and ducting			••••	•••	•••	••••		••••	•••		
Fire retardant production parts								••••			
Medical applications				••••							
Jigs / fixtures / tools			• • •	•••	••••	••••			•••		
Investment casting patterns							••••				
Gaskets, seals and hoses	••••	••••									
Footwear	••••	•••									

Ranking: Ratings are relative to other materials presented.




^{*} Please see the product datasheet for more detailed information.

	Sintered Part Density (g/cm³)	Flexural Modulus (MPa)	Flexural Strength (MPa)	Tensile Modulus (MPa)	Tensile Strength (MPa)	Elongation at Break (%)	Impact Strength (J/m) Unnotched Izod Notched Izod	Heat Deflection Temperature (°C) @ 0.45 MPa @ 1.82 MPa	Flammability	Hardness
	ASTM 792	ASTM D 790	ASTM D 790	ASTM D 638	ASTM D 638	ASTM D 638	ASTM D 256	ASTM D 648	UL 94	ASTM D2240
sPro Compatible Material	Properties									
DuraForm TPU*	0.78	6.0	-	5.3	2.0	220 %	:	-	-	59A
DuraForm Flex*	-	5.9	48	5.9	1.8	110 %	-	-	-	45-75A
DuraForm EX	1.01	1310	46	1517	48	47 %	74 1486	188 48	НВ	74D
DuraForm PA	1.03	1387	48	1586	43	14 %	32 336	180 95	НВ	73D
DuraForm GF	1.49	3106	37	4068	26	1.4 %	41 123	179 134	НВ	77D
DuraForm HST	1.20	4400-4550	83-89	5475-5725	48-51	4.5 %	37.4 310	184 179	НВ	75D
CastForm PS	0.86	-	-	1604	2.84	-	< 11 14	:	-	-
DuraForm FR1200*	1.02	1770	62	2040	41	5.9 %	25 233	180 94	НВ	76D

^{*} Material compatible only with sPro™ 60 HD-HS.

ProX Compatible Material Properties											
DuraForm ProX PA	0.95	1650	63	1770	47	22 %	45 644	182 97	НВ	73D	
DuraForm ProX GF	1.33	3120	60	3720	45	2.8 %	48 207	180 129	НВ	73D	
DuraForm ProX HST	1.12	3430	75	4123	44	4.3 %	55 307	183 171	НВ	73D	
DuraForm ProX EX BLK	1.02	1360	51	1570	43	60 %	75 3336	193 57	НВ	76D	
DuraForm ProX AF+	1.31	3710	64	4340	37	3 %	54 255	182 174	НВ	78D	
DuraForm ProX FR1200	1.03	1720	61	2010	45	8 %	24 278	180 94	НВ	77D	

www.3dsystems.com



Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.